

# Denka Natmic AF-S

## Alkali-Free Liquid Accelerator for Sprayed Concrete Application

### Description

**Denka Natmic AF-S** is an alkali-free accelerator for sprayed concrete that can be used for civil engineering works such as road and railways tunnels, headraces, and mines. The accelerator is applied when initial rock support is needed or where a permanent lining will be placed.

### Uses



Rock support in tunnels and mines



Slope stabilization



TBM Tunnel Linings

### Advantages

- Quick setting time and high initial strength.
- Development of high compressive strength after 28 days and excellent long-term durability.
- Very low dust emissions.
- Very low rebound.
- Low alkali content (<1%)

### Physical Properties

Color/Form	White / Suspension
Density, g/cm <sup>3</sup>	1.30 – 1.50
pH	2.0 – 3.0
Viscosity at 20°C (mPa s)	500 – 2000
Alkali content (Na <sub>2</sub> O equiv.%)	<1

### Dosage and water to binder ratio

The dosage of **DENKA NATMIC AF-S** depends on the temperature, cement reactivity, setting time, strength development, and required thickness of the layers. The dosage of **NATMIC AF-S** ranges from 3 to 12% of the binder weight.

When **DENKA NATMIC AF-S** is used for wet-mix sprayed concrete, the water to binder (cement or cement plus fly ash and/or silica fume) ratio should be below 0.5 and preferably <0.45.

The dosage of the product should be optimized for the spraying process after spraying trials.

### Packing Size

<b>NATMIC AF-S</b>	280kg / drum
	1200kg/tote tank

### Cleaning

Wash all equipment with water after used.

### Technical Support

Denka offers a technical support package to specifiers, end-user and contractors, as well as on site technical assistance.

### Storage

**DENKA NATMIC AF-S** has a shelf life of 6 months in unopened containers, kept in a dry store. In high humidity locations, the shelf life may be reduced.

230303

## Precautions

- Refer to the Safety Data Sheet (SDS) before use.
- Do not mix with other accelerators or chemical admixtures because chemical reactions may occur that cause the product to separate or precipitate. Particular care should be taken with nitrites, thiosulfates, and rhodonite compounds, which will generate poisonous gas when mixed with **DENKA NATMIC AF-S**.
- **DENKA NATMIC AF-S** should not be mixed with concrete containing blast furnace slag (BFS) as this will generate hydrogen sulfide.
- Protective wear (goggles, mask, gloves, and rubber boots) should be worn during handling.
- The dosing pump and other equipment should be acid-resistant because **DENKA NATMIC AF-S** is acidic.
- Do not dispose of **DENKA NATMIC AF-S** in drains.
- The product in open containers should be used up completely or the container should be resealed for storage.

## Additional Information

**Denka Construction Solutions Malaysia Sdn Bhd** offers a wide range of complementary products, which includes waterstops, waterproofing products, grouts, anchors, specialized flooring products. In addition, a wide range of products formulated for repair and refurbishment of spalled concrete are available.



**Denka Construction Solutions Malaysia Sdn Bhd**

(591858-U)

No. 18, Jalan Utas 15/7, Seksyen 15,  
40200 Shah Alam, Selangor Darul Ehsan, Malaysia

Tel: +603 5510 8810 Fax: +603 5518 8202

[www.denka-cs.com](http://www.denka-cs.com)

## Limitation of Liability

The information contained in this brochure provides general advice for potential customers for **DENKA** about the basic properties and characteristics of various **DENKA** products (hereafter known as "the Product Information"). **DENKA** makes no warranty or representation as to the entire accuracy or completeness of the Product Information in the brochure. Nothing in this brochure will be deemed to create any express or implied warranty of merchantability, fitness for a particular purpose or infringement of any intellectual property rights. Each user of the Product Information and **DENKA** products assumes their own responsibility to properly determine the manner and suitability of use of the Product Information and **DENKA** products in its own operations. The user should exercise proper care in considering the Material Safety Data Sheet, Product Information and any other technical information provided by **DENKA** including descriptions of the conditions of use, warnings and other cautionary instructions. **DENKA** reserves the right to change the Product Information from time to time at its discretion and without notice.